



AT&T Bell Laboratories
600 Mountain Ave.
Murray Hill, NJ 07974

subject: EIA 564 Intercept Test

date: October 19, 1994

from: John P. Francy
RM 1B401
Voice (908) 582-2490
Fax (908) 582-6290

A laboratory test of 2 Mil Static Intercept film was performed using the Electronic Industry Association (EIA) #564 test method (Standard method for Chemical Compatibility of Polycarbonate by Stress Cracking Evaluations).

The results are shown in table 1 and indicate the Static Intercept material does not cause any measurable crazing under the most severe conditions.

Static Intercept EIA 564 Results
Stress (PSI)

Temp F	1000	1700	2000	2500	3400
165	0	0	0	0	0
158	0	0	0	0	0
120	0	0	0	0	0
73	0	0	0	0	0

0= No crazing observed.